

ООО «Полимер Экспорт» промышленные лакокрасочные покрытия

8 (4932)773-503





Release date: 01.10.2024 Manufacturer: Russian Federation TY 20.30.11-017-69372620-2022

Enamel IKHOLZ W.21MQ

Water based acrylic enamel for interior work

CERTIFICATE

State Registration Certificate № RU.8.08.09.008.E.000311.10.22 от 04.10.2022 г. Declaration of Conformance № POCC RU Д-RU.PA01.B.36551/22 от 12.10.2022 г. Safety data sheet of chemical products from 14.11.2022.

DESCRIPTION

Single - component water based acrylic enamel.

FIELDS OF APPLICATION

Water-based acrylic enamel is designed for decorative finishing of wooden surfaces as well as painting pre-primed MDF boards. Articles covered with enamel should be used indoors avoiding high humidity, direct contact with water and other aggressive environments. Enamel has excellent decorative properties, high adhesion and varying degrees of gloss.

Enamel is available as standard in white, toning is possible if necessary. The first layer of enamel can be used as a primer layer. Enamel does not contain aromatic solvents, does not have a sharp odour.

TECHNICAL DATA

Colour	White*, basis A, basis C
Gloss	G20: 20-36 G40: 36-41
Surface	Uniform matte or glossy surface without pinholes, pores and pebbles.
Viscosity B3-246 (spindel №4)	50-70 s
Coverage, no more	50 g/m ²
Density	1,15-1,30 g/cm ³
Spread:	
Primer	150 -170 g/m ²
Finishing	110 - 130 g/m ²
Open time to grade 3 (20±2)°C, no more	60 min
Thinner	Water
Stacking resistance	In 120 min
* Standard in white	

^{*} Standard in white

INSTRUCTION FOR USE

Wood surface must be free of all possible contaminants: dust, grease and resin. The wood is then sanded with No. 150 sandpaper manually or with a grinding machine with the required degree of abrasiveness (No. 150). After grinding, the surface is primed. For the primer layer, prime can be thinned with water about 5-10 % if necessary. Use pneumatic spraying or combined application units for priming. An hour after applying the primer layer, the surface must be sanded with sandpaper No. 320 to remove raised piles of wood. Use pneumatic spraying or combined application units for finishing. In two hours after application stacking of products is possible.











ООО «Полимер Экспорт» промышленные лакокрасочные покрытия

8 (4932)773-503





CONDITIONS

The temperature in the shop when applying the material should be 20-24°C, humidity not more than 80%. To avoid physical damage (cracking, "orange peeling" and loss of shine) on the coating when applying and drying products avoid drafts.

APPLICATION

Preparing Mix thoroughly

Automatic painting Operation viscosity: 50-70 s

Nozzle diameter: 0,9 mm Initial pressure: 25-45 atm High-pressure spray: 1,0-1,5 atm

Air spraying Operation viscosity: 50-70 s

Water

Nozzle diameter: 1,4-1,8 mm Initial pressure: 4-5 atm

Thinner Water

Cleaning Clean the equipment with water after use according to the manual.

PACKAGE SIZE

Plastic bucket 20 l: basis

20 kg

Cleaner

STORAGE

Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Keep from sunlight and moisture at temperature from 5°C to +40°C. DO NOT FREEZE!

GUARANTED STORAGE LIFE

Expire date is 12 months in case if delivery and storing rules are followed. After expire date shouldn't be used without tests.

HEALTH AND SAFETY

Observe precautionary measures. Use means of individual protection (respirators, gloves, glasses, etc.). Use under well ventilated conditions. Use in places without sources of open fire and ignition only. Avoid skin or eyes contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water, don't use solvents. If eyes contact, rinse with clean water for at least 10 minutes, consult a doctor. In case of ingestion consult a doctor.

RECYCLING

Packing materials are recycled as consumer waste.







